



UK DISTRIBUTORS OF
REINHARDT-TECHNIK
 Metering & Mixing
 Dispensing Systems

Bonham Drive, Eurolink Industrial Estate
 Sittingbourne, Kent. ME10 3RY
 Tel 01795 427888 Fax 01795 479685
 Email sales@eurobond-adhesives.co.uk
 Web www.eurobond-adhesives.co.uk

EB6110G Foamed Acrylic Tape - Technical data sheet

TECHNICAL DESCRIPTION	UNIT OF MEASURE		TECHNICAL VALUE	
CARRIER			ACRYLIC FOAM	
ADHESIVE			ACRYLIC	
COLOUR			GREY	
THICKNESS	mm	ins	1.1(±0.1)	0.043(±0.004)
RELEASE LINER			RED PE	
DENSITY OF FOAM	Kg/m ³	lbs/ft ³	780	49
180° PEEL ADHESION ASTM D-3330 (Stainless steel, room temp)	g/25mm	lbs/in	3900	8.7
TENSILE ADHESION (T-BLOCK TEST) ASTM D-987 (aluminium, room temp)	g/cm ²	lbs/in ²	6000	85
DYNAMIC SHEAR ASTM D-1002	g/cm ²	Lbs/in ²	To stainless Steel Room Temp after 20 mins	
			≥ 3500	50
			To stainless Steel Room Temp after 24 hours	
			≥ 6000	85
TEMPERATURE RESISTANCE SHORT TERM	°C	°F	160	320
TEMPERATURE RESISTANCE LONG TERM	°C	°F	100	212
LOW TEMPERATURE RESISTANCE	°C	°F	-40	-40
U.V RESISTANCE			GOOD	

22.02.16

No liability is accepted for any injury, loss or damage arising directly or indirectly from the use of the Company's products or from the use of information given in our publications, which is intended to serve as a guide only. Customers should satisfy themselves by appropriate trials that the products are suitable for their intended use.

