



UK DISTRIBUTORS OF
REINHARDT-TECHNIK
Metering & Mixing
Dispensing Systems



Bonham Drive, Eurolink Industrial Estate
Sittingbourne, Kent. ME10 3RY
Tel 01795 427888 Fax 01795 479685
Email sales@eurobond-adhesives.co.uk
Web www.eurobond-adhesives.co.uk

Technical Data Sheet

PENLOC 1:1R - Low-odour and Non-flammable Toughened Acrylic Adhesive

PENLOC 1:1R is a fast curing high strength, toughened acrylic adhesive, which will bond metals, plastics, wood, glass and composites to themselves or in any combination.

PENLOC 1:1 R is a medium viscosity and can be used bead on bead direct from the cartridge without the need of an additional mixer. This unique property allows stop-start usage without wastage or mixer blockage.

TECHNICAL DATA

Colour: Blue
Resin: Methacrylate

UNCURED PROPERTIES

Viscosity (Brookfield LVT): 4000 mPa*s
Flash point : >80 ºC
Pot-Life: 3 min.

CURING

Handling Strength: 3 -5 minutes
Full Strength: 1 hour

SHEAR STRENGTH

Steel: 20 N/mm
Brass: 20 N/mm
Aluminium: 18.1 N/mm
PVC: 2.6 N/mm
PA: 6.2 N/mm

CURED PROPERTIES

Temperature resistance: -20 to 120 ºC
Hardness Shore D: 65 to 75
Shrinkage: 7.6%

08.08.16

No liability is accepted for any injury, loss or damage arising directly or indirectly from the use of the Company's products or from the use of information given in our publications, which is intended to serve as a guide only. Customers should satisfy themselves by appropriate trials that the products are suitable for their intended use.

