

# Technical Datasheet

## Vitralit® VBB-1



### Product Description

Vitralit® adhesives are one-component, solvent-free radiation-curing adhesives. The advantages are very short curing times, good adhesion to a variety of substrates, and easy handling. Vitralit® products are used in electronics, medical applications, optics and for fixing parts in general.

Vitralit® VBB-1 is a UV/visible light curable, multi-substrate bonder that exhibits excellent peel strength. The cured Vitralit® VBB-1 is optically clear, exceptionally flexible and demonstrates outstanding elongation. Vitralit® VBB-1 is recommended for applications where a tough, durable and moisture resistant bond is required. Because of the ability to bond to many substrates and ability to withstand the stress of thermal cycling. Vitralit® VBB-1 is very well suited for use as a UV curable potting composition.

### Curing Properties

UV-A	VIS	Thermal curing	Activator curing
✓	✓	-	-

✓ suitable      - not suitable

The product cures within seconds with radiation in the UV-A - range (320 nm - 390 nm). For rapid and high quality crosslinking we recommend the UV devices manufactured by Dr. Hoenle AG, which complement our adhesive technology.

UV-curing (Hoenle Discharge lamp, 320-450nm)		
Intensity [mW/cm <sup>2</sup> ]	Layer thickness [mm]	Time [sec]
60	0,5	10

VIS-curing (Hoenle LED Spot 100, 405nm)		
Intensity [mW/cm <sup>2</sup> ]	Layer thickness [mm]	Time [sec]
100	0,5	60

To obtain full cure at least one substrate must be transparent to the recommended wavelength. The curing speed will depend on the intensity of light, light source, the exposure time, and the light transmittance of the substrate. Increased mechanical properties are achieved after 12 hours.

### Technical Data

Resin  
Appearance

urethane acrylate  
transparent

# Technical Datasheet

## Vitralit® VBB-1



### Uncured material

Viscosity [mPas] (Brookfield LVT, 25°C, Sp 4, 30rpm) <i>PE-Norm 001</i>	1 000 - 1 500
Density [g/cm³] <i>PE-Norm 004</i>	1,1
Flash point [°C] <i>PE-Norm 050</i>	>93
Refractive index [nD20] <i>PE-Norm 018</i>	1,4718

### Cured material

Hardness shore A <i>PE-Norm 006</i>	50 - 70
Temperature resistance [°C]	-50 - 150
Shrinkage [%] <i>PE-Norm 031</i>	<5
Water absorption [mass %] <i>PE-Norm 016</i>	<1

Glass transition temperature DSC [°C] <i>PE-Norm 009</i>	-45
Coefficient of thermal expansion [ppm/K] below Tg <i>PE-Norm 017</i>	80
Coefficient of thermal expansion [ppm/K] above Tg <i>PE-Norm 017</i>	329

Young's modulus E [MPa] <i>PE-Norm 056</i>	1
Tensile strength [MPa] <i>PE-Norm 014</i>	3
Elongation at break [%] <i>PE-Norm 014</i>	353
Lap shear strength (glass/glass) [MPa] <i>PE-Norm 013</i>	6
Lap shear strength (glass/Al) [MPa] <i>PE-Norm 013</i>	3
Lap shear strength (glass/steel) [MPa] <i>PE-Norm 013</i>	3
Lap shear strength (PC/PC) [MPa] <i>PE-Norm 013</i>	2
Lap shear strength (PC/PMMA) [MPa] <i>PE-Norm 013</i>	3
Lap shear strength (PC/FR4) [MPa] <i>PE-Norm 013</i>	2

# Technical Datasheet

## Vitralit® VBB-1



### Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Cartridge	at room temperature max. 25°C	at room temperature max. 25°C	at delivery min. 6 months max. 12 months
other packages			

***\*Store in original, unopened containers!***

### Instructions for Use

#### Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IPA.® Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

#### Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

After application, bonding of the parts should be done quickly. Vitralit® adhesives cure slowly in daylight. Therefore, we recommend to expose the material to as little light as possible and the use of opaque hose lines and dispensing needles.

For safety information refer to our safety data sheet.

### Disclaimer

The product is free of heavy metals, PFOS and Phthalates and is conform to the EU-Directive 2017/2102/EU "RoHS III".

**THE VALUES NOTED IN THIS TECHNICAL DATA SHEET ARE TYPICAL PROPERTIES AND ARE NOT MEANT TO BE USED AS PRODUCT SPECIFICATIONS.**

The information contained in this data sheet is believed to be accurate and is provided for information only. Eurobond Adhesives Limited makes no representation or warranties of any kind concerning this information. It is the user's responsibility to determine the suitability of this product for any intended use. Eurobond Adhesives Limited does not assume responsibility for test or performance results obtained by the user. The user assumes all risk and liability connected with the use of this product.

# Technical Datasheet

## Vitralit® VBB-1



The user should adopt such precautions and use guidelines as may be advisable for the protection of property and persons against any hazards that may be involved in this product's handling or use. Eurobond specifically disclaims any liability for consequential or incidental damages of any kind arising from the handling or use of this product. The information contained in this Technical Data Sheet offers no assurance that the product use, application, or process will not infringe on existing patents or licenses of others.