



UK & IRELAND DISTRIBUTORS OF  
**REINHARDT-TECHNIK**  
 Machines for the application of adhesives & sealants  
**PANACOL**  
 Adhesive systems



Bonham Drive, Eurolink Industrial Estate  
 Sittingbourne, Kent. ME10 3RY  
 Tel 01795 427888 Fax 01795 479685  
 Email [sales@eurobond-adhesives.co.uk](mailto:sales@eurobond-adhesives.co.uk)  
 Web [www.eurobond-adhesives.co.uk](http://www.eurobond-adhesives.co.uk)

## Eurobond QuickFix

### PRODUCT DESCRIPTION

Eurobond QuickFix is a non hazardous, high quality fast curing 2-part MS Polymer adhesive supplied in a convenient 250ml cartridge to fit most sealant applicator guns. It is suitable for applications where a quick cure and high strength permanently elastic bond is required or for applications where the bond design does not allow the normal penetration of atmospheric moisture. Apply in temperatures between +5°C and +40°C. QuickFix exhibits good resistance to water, UV, aliphatic solvents, mineral oils, grease, diluted inorganic acids and alkalis.

### Technical Data

|                          |                                                      |
|--------------------------|------------------------------------------------------|
| Composition:             | MS Polymer                                           |
| Viscosity:               | Paste                                                |
| Specific gravity:        | 1.4g/cm <sup>3</sup>                                 |
| Curing System            | Chemical 1:1 mix ratio component A with component B. |
| Open time                | 21°C/50% RH Ca 10 minutes.                           |
| Pot life                 | 21°C/50% RH Ca 5 minutes.                            |
| Time to cure             | 21°C/50% RH Ca 4 hours.                              |
| Shore A Hardness         | 40 Shore A                                           |
| Temp. resist fully cured | -40°C to +90°C                                       |
| Elasticity Modulus       | 100% (DIN 53504) 1.3MPa                              |
| Tensile strength         | (DIN 53504) 2.2MPa                                   |
| Elongation at break      | (DIN 53504) 350%                                     |
| Colour                   | Light Grey                                           |
| Shelf Life               | 6 months when stored between +5°C and +25°C          |

### Surfaces

All usual building surfaces, most metals, polyesters & many plastics. DO NOT use on PE, PP, PTFE or ABS.

### PRECAUTIONS

Customers should satisfy themselves by appropriate trials that the products are suitable for their intended use. Poor resistance to aromatic solvents, concentrated acids & chlorinated hydrogen.

For handling and safety precautions, please refer to the Material Safety Data Sheets and the general handling instructions.

No liability is accepted for any injury, loss or damage arising directly or indirectly from the use of the Company's products or from the use of information given in our publications, which is intended to serve as a guide only. Customers should satisfy themselves by appropriate trials that the products are suitable for their intended use.

