



UK DISTRIBUTORS OF
REINHARDT-TECHNIK
Metering & Mixing
Dispensing Systems



Bonham Drive, Eurolink Industrial Estate
Sittingbourne, Kent. ME10 3RY
Tel 01795 427888 Fax 01795 479685
Email sales@eurobond-adhesives.co.uk
Web www.eurobond-adhesives.co.uk

Eurobond Glass Bonder (Ultimate Strength) - Technical Data Sheet

Chemical Type:	Methacrylate Ester
Appearance (Uncured):	Colourless
Components:	One component
Viscosity:	Medium
Cure:	Visible/UV Curing

Typical Application

Eurobond Glass bonder (Ultimate strength) is a UV/visible light curing adhesive, designed for bonding glass and glass to metal applications. The cured adhesive exhibits extraordinary high strength. Eurobond Glass bonder is fast curing, transparent and easy to use.

Typical Properties of Uncured Material

Gravity @ 25°C	1.06
Viscosity (Medium Viscosity) 25°C, mPa•s (cp)	250 – 3000cp
Colour:	Clear
Flash Point:	>93°C
Fixture time (100 mW/cm ² @ 365nm)	≤15LMS
Refractive Index:	1.48 – 1.51

Typical Properties of Cured Material

Temperature (°C)	-54 +120
Hardness Shore D	65
Tensile Strength (Mpa)	≥12
Volumetric Shrinkage %	≤8.7
Coefficient of Thermal Conductivity W/(m•K)	0.10

Cure Properties

Eurobond Glass bonder can be cured by irradiation with UV/Visible light of sufficient intensity. The Cure rate and ultimate depth of cure will depend on light intensity, the spectral distribution of the light source, the exposure time and the light transmittance of the substances. Discuss with the Eurobond Technical team the most appropriate curing light source to use.

The user should conduct suitable testing to satisfy themselves that the adhesive meets the specific performance criteria for the application.

Usage

1. This product is light sensitive; exposure to daylight, UV light and artificial lighting should be kept to a minimum during storage and handling.
2. For best performance bond surfaces should be clean and free from grease.
3. Cure rate is dependent on lamp intensity, distance from lamp source, depth of cure needed or bond line gap and light transmittance of the substrate through which the radiation must pass.
4. Cooling should be provided for temperature sensitive substrates such as thermoplastics.
5. Excess uncured adhesive can be wiped away with organic solvent (e.g. IPA wipes)
6. Bonds should be allowed to cool before subjecting to any service loads.

Storage

It should be kept in an unopened container in a cool and dry location.

Optimal Storage:

8°C to 21°C. Storage below 8°C or greater than 21°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Keep away from children.

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the users responsibility to determine the suitability for the uses purpose of any product methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof.

17.03.20

No liability is accepted for any injury, loss or damage arising directly or indirectly from the use of the Company's products or from the use of information given in our publications, which is intended to serve as a guide only. Customers should satisfy themselves by appropriate trials that the products are suitable for their intended use.

